

TDS: QW2K



PRODUCT NAME

QW2K

DATE CREATED

01/01/2021

LAST REVIEWED 11/02/2021

DESCRIPTION

QUICKWALL **QW2K WATERPROOFING** Two-component, flexible cementitious mortar

SUITABLE FOR

Waterproofing balconies, terraces, bathrooms and swimming pools.

APPLICATION & DRY TIME

Trowel or by brush

Leave adequate drying time of 24hours between coats

**Refer to QW2K application guideline sheet for full application instructions.*

TECHNICAL DATA

Consistency of mix: Slurry brush on or trowelable.

Mixing ratio: comp. A: comp. B = 1 : 1.

Pot life of mix: approximately 1 hour.

Application temperature range: from +5°C to +35°C.

Minimum applicable thickness: 1.8 mm in 2 coats.

Classification: EN 1504-2 - coating (C) principles PI, MC and IR and EN 14891 norm.

EMICODE: EC1 R Plus - very low emission.

STORAGE

6 months comp. A, 12 months comp. B from date of purchase.

CONSUMPTION

– trowel: 1.7 kg/m² per mm of thickness;

– brush: 2.2 kg/m² per mm of thickness.